



CSI Code: 02760

No. 227-3

JULY 2004
(Supersedes January 2004)

SEALEX® E-Z

One-Part, Flexible, Cold-Applied, Traffic Loop Sealant

DESCRIPTION

SEALEX E-Z is a one part, flexible, and fast drying traffic loop protector and sealant. While totally encapsulating sensitive detection wiring to add greater protection, SEALEX E-Z provides superior joint sealing properties.

SEALEX E-Z can even be applied into damp joints. (No standing water). It bonds tenaciously to both Portland cement and asphalt concrete pavements. Sidewall adhesion and flexibility characteristics are retained during cold winter temperatures. SEALEX E-Z will not flow from joints or be picked up by vehicular traffic in hot weather.

TECHNICAL DATA

Consistency: Heavy Syrup-Self Leveling
Weight Per Gallon: 8.3 Lbs. (3.74kg)
Color: Black

SHELF LIFE - 6 months when stored unopened, in original container. Storage temperature should not exceed 90° F (32° C).

FEATURES AND BENEFITS

- Self leveling/No tooling required
- Easy to use/One-component, pours directly from the container
- Totally encapsulates wiring/Protects and waterproofs cabling
- Can be applied to damp joints/Increased productivity
- Fast drying/Opens to traffic immediately with proper joint design
- Outstanding sealant characteristics/ Year-round seasonal performance
- High arc resistance/No threat of electrocution
- Safe to use/No special protective gear needed
- Gives off no dangerous vapors/No special ventilation or respirators required
- Cleans up with water/Easy to maintain

PACKAGING & STORAGE

1 Gallon (3.79 Liter) Container
5 Gallon (18.93 Liter) Pail
55 Gallon (208.45 Liter) Drum

COVERAGE		LINEAR FEET PER GALLON		
DIMENSIONS	1/2"	1"	1-1/2"	2"
1/4"	154	77	51	39
3/8"	103	51	34	26
1/2"	77	39	26	20

CONTINUED ON REVERSE SIDE...

TEST		RESULTS
Total Solids by weight, % minimum	ASTM D 2834	70
Tack Free Time, h, max.	ASTM C 679	2
Rheological Properties	ASTM C 639 TYPE 1	Smooth surface
Extrusion Rate, mL/min. minimum	ASTM C 1183	Greater than 50
Hardness shore A, minimum	ASTM D 2240	Greater than 10
Penetration @ 77° F (25° C), max.	ASTM D 5	70
Dielectric Strength, 60 Hz, Short Time test, Electrode 1 in air @ 25° C kV/mm, minimum	ASTM D 149	Greater than 13.8
Flex @ 19° F (-7° C), 1 inch, 90° Bend	ASTM D 5329	Pass

APPLICATION

Apply SEALEX E-Z when the air and pavement temperatures are above 45° F (7°C). Do not apply if rain is forecast or imminent with 24 hours.

Surface Preparation...The sawed loop should be clean and free of standing water, however SEALEX E-Z can adhere to damp joints.

Application Method...MIX WELL BEFORE USING. Pour sealant directly from the one-gallon unit or from any appropriate pouring container. Once applied, a follow-up should be done with a soft rubber, U-shaped squeegee to form a wipe zone of approximately 3-4 inches (76.2-101.6mm) wide along the crack/joint and flush with the highway or pavement surface.

SEALEX E-Z will become tack-free within two hours. To help insure that traffic will not pick up the sealant prior to full cure, the material can be recessed 1/8" below the pavement surface. Dust with cement dust, cover with a 2-ply toilet paper, or spray with a detackifier to aid in reducing any potential for tracking.

Clean up...Use water for clean up before product cures. Once material has cured, use a solvent-based cleaner.

PRECAUTIONS

KEEP FROM FREEZING. Storage temperatures should not exceed 90° F (32° C). Do not apply if rainfall is forecast or imminent. Do not apply if air and surface temperatures are expected to fall below 45° F (7° C) within 2 days after application.

HEALTH AND SAFETY

Refer to Material Safety Data Sheet for complete health and safety information.

FOR THE MOST CURRENT PRODUCT INFORMATION, VISIT OUR WEBSITE:
www.wrmeadows.com



LIMITED WARRANTY

“W. R. MEADOWS, INC. warrants at the time and place we make shipment, our material will be of good quality and will conform with our published specifications in force on the date of acceptance of the order. Read complete warranty.” Copy furnished upon request.

Disclaimer

The information contained herein is included for illustrative purposes only, and to the best of our knowledge, is accurate and reliable. W. R. MEADOWS, INC. cannot however under any circumstances make any guarantee of results or assume any obligation or liability in connection with the use of this information. As W. R. MEADOWS, INC. has no control over the use to which others may put its product, it is recommended that the products be tested to determine if suitable for specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect or engineer, contractor and owner for the design, application and proper installation of each product. Specifier and user shall determine the suitability of products for specific application and assume all responsibilities in connection therewith.