



BRICKFORM® Color Hardener™

Concrete Topping and Hardener

BRICKFORM Color Hardener is an engineered blend, used to color the surface of new concrete. When applied, a dense layer is formed, making the concrete surface more abrasion and impact resistant. BRICKFORM Color Hardener is available in 40 standard colors and custom color matching is available.

FEATURES

- Non-Fading
- Denser, More Durable Surface
- Improved Abrasion Resistance
- Can Be Antiqued And Stained

PRODUCT DESCRIPTION • BRICKFORM Color Hardener is manufactured with the finest UV-resistant pigments and premium aggregates available. BRICKFORM Color Hardener is designed to work with imprinting tools to produce clear, sharp impressions that enhance the finished appearance of any new hardscape. When properly applied and troweled into newly placed, fresh concrete, it forms a colored concrete surface that is resistant to weathering, wear and normal abrasion.

USES • BRICKFORM Color Hardener is used in the construction of new concrete flatwork and floors. It can be troweled and broomed, or imprinted, using BRICKFORM Texture Mats™ and BRICKFORM Liquid Release™. Create the look of expensive materials such as handset tile, brick or quarried stone with by using a powdered release like BRICKFORM Antique Release™, in a contrasting color. The color-hardened surface can also be stained, after the concrete has been allowed to cure for approximately 28 days, with BRICKFORM Blush-Tone Acid Stain™. Please get a copy of the appropriate Technical Information Sheet and MSDS for each product before attempting to use.

LIMITATIONS • BRICKFORM Color Hardener is for use only with freshly poured, still-plastic, concrete surfaces.

COLORS • BRICKFORM Color Hardener is available in 40 standard colors. Custom colors and color matching are also available.

PACKAGING • BRICKFORM Color Hardener is packaged in convenient 60-pound, moisture-resistant pails. This type of packaging gives the material a shelf life of at least one-year, double the life of bagged color hardeners.

COVERAGE • For most applications of darker colors, BRICKFORM Color Hardener should be applied at the rate of 60 or more pounds (27 kg) per 100 square feet (9.29 m²). Light pastel colors generally require heavier applications of up to 60 pounds (27 kg) per 80 square feet (7.43 m²). When a lightly sandblasted surface for decorative purposes is required, a minimum of 90 pounds (40.5 kg) per 100 square feet (9.29 m²) should be applied.

STORAGE • Store in a safe place. Keep containers tightly sealed. Shelf life is approximately 12 months.

CAUTION • KEEP OUT OF REACH OF CHILDREN. Before using or handling, read the Material Safety Data Sheet and Warranty. DO NOT TAKE INTERALLY. Avoid contact with eyes and skin. When working with or near this product, all personnel must wear MSHA-NIOSH approved respirators (refer to OSHA standards in 29 CFR 1910.134). Prolonged, unprotected exposure may result in non-reversible Silicosis or Lung Cancer. Avoid inhalation and use local exhaust to keep exposures below OSHA PEL's for silica and nuisance dusts. Avoid contact with skin and eyes. Wear rubber gloves and aprons to protect skin and wear safety eye goggles. Wash splatters from skin immediately. Use good hygiene when handling this product and wash and bathe after each use. Close containers after each use. Be sure to wash clothing after each use.

PREPARATION OF SUB GRADE • The subgrade must be uniformly graded, compacted and moistened, but free of standing water. Avoid placing concrete over soft, frozen, or muddy spots. Follow professional standards and practices, including those published by the American Concrete Institute (ACI).

PREPARATION OF CONCRETE • BRICKFORM strongly recommends representative jobsite samples. Individuals who will be performing the work should use the specified materials, as well as the finishing and curing techniques that will be used on the project. The concrete should be designed to meet the strength and finishing requirements of the project with a minimum cement content of 5 1/2 sacks per cubic yard (.765 m³) and a maximum slump of 4 inches (10.10 cm). BRICKFORM Color Hardener is compatible with most water-reducing, set-retarding and air-entraining concrete admixtures. Avoid using admixtures containing calcium chloride, or the addition of calcium chloride in any form, to the concrete for acceleration during cold weather. All fine and course aggregates must be non-reactive and free of deleterious material.

APPLICATION • Protect surrounding areas where color is not desired. Using protective gloves, reach down into each bucket and remix the material that may have settled during transporting and storage. Multiple buckets should be intermixed. Apply BRICKFORM Color Hardener after the concrete has been placed, screeded, floated and excess bleed water has disappeared from the concrete surface. BRICKFORM Color Hardener should be applied, using the broadcast method, at the rate of at least 60 pounds (27 kg) per 100 square feet (9.29 m²) in two applications. Pastel shades or light colors may require up to 60 pounds (27 kg) per 80 square feet (7.43 m²). The first application requires at least 40 pounds (18 kg) per 100 square feet (9.29 m²). The second application should give complete and uniform coverage. Float the concrete surface after the first application, but do not trowel. After the second application of BRICKFORM Color Hardener, the concrete can be finished as specified. Maintain consistent finishing techniques and avoid hard-troweling for the most uniform color results. Over-troweling will discolor the concrete. Additional water should not be applied to the concrete surface during finishing. All water required will come from the concrete.

CURING • The use of a clear, non-staining acrylic or wax curing compound is recommended. Do not cure with plastic sheeting, membrane paper or water misting. Avoid the use of sodium-silicone-type hardeners. Products not recommended could cause discoloration or mottling of the colored surface.

SEALING • After the concrete has been allowed to cure for 28 days, protect the surface with BRICKFORM Gem-Seal, Poly-Astic, Poly-Seal, Safety-Seal, or Satin-Seal. Please get a copy of the appropriate Technical Information and Material Safety Data Sheet before attempting to use these products. Once sealed, protect the surface from foot traffic for 24 hours and vehicular traffic for 5 days.

MAINTENANCE • The sealed surface should be inspected periodically for areas of thin or traffic-worn sealer. Brickform recommends the application of Dura-Wax as a sacrificial coating on interior surfaces. Reapply as needed, according to the appropriate Technical Information Sheet. If traces of efflorescence are present, this should first be eliminated with a gentle cleaner such as BRICKFORM Antique Release/Efflorescence Remover, according to the *BRICKFORM Antique Release/Efflorescence Remover Technical Information Sheet*.

WARRANTY • This product is not intended for public use and is intended for use by licensed contractors and installers, experienced and trained in the use of these products. It is warranted to be of uniform quality, within manufacturing tolerances. The manufacturer has no control over the use of this product, therefore, no warranty, expressed or implied, is or can be made either as to the effects or results of such use. In any case, the manufacturer's obligations shall be limited to refunding the purchase price or replacing material proven defective. The end user shall be responsible for determining product's suitability and assumes all risks and liability.

PLAN SPECIFICATION

BRICKFORM® Color Hardener™ Suggested Short Form Specification: All concrete flatwork designated in the plans and specifications as having a colored & hardened surface shall be color hardened with BRICKFORM Color Hardener, manufactured by BRICKFORM, 800-483-9628, Rancho Cucamonga, CA 909-484-3399, in accordance with the **BRICKFORM Color Hardener Technical Information Sheet**, using _____ color and a minimum of _____lbs. Per 100 square feet (_____kg per 9.29 m²). After the concrete has been allowed to cure for 28 days, all surfaces shall be sealed with BRICKFORM Gem-Seal™, or Poly-Seal™, BRICKFORM Safety-Seal™, or BRICKFORM Satin-Seal™ in accordance with their corresponding Technical information Sheet. All products shall be manufactured by BRICKFORM, 800-483-9628, Rancho Cucamonga, CA 909-484-3399. BRICKFORM Color Hardener meets ASTM STDS – abrasion resistance and PSI.

ORDER SPECIFICATIONS

Product

Color Hardener

Shipping Weight:

65 lbs (29.25 kg)

Item No. Color

- CH-100 Dark Gray
- CH-115 Venetian Pink
- CH-200 Medium Gray
- CH-250 Oyster White
- CH-300 Nutmeg
- CH-310 Cream Beige
- CH-320 Golden Sandstone
- CH-325 Sandstone
- CH-330 Coconut
- CH-350 Desert Tan
- CH-375 Buff Tan
- CH-425 Autumn Brown
- CH-500 Tile Red
- CH-515 Sunbaked Clay
- CH-525 Dusty Rose
- CH-550 Brick Red
- CH-575 Victorian Red
- CH-600 Light Gray
- CH-615 Stone Gray
- CH-625 Dover Blue
- CH-650 Smokey Blue

Container Size:

5-Gallon Buckets (18.925 L)

Item No. Color

- CH-700 Terra Cotta
- CH-735 Cappuccino
- CH-810 Walnut
- CH-820 Muted Green
- CH-825 Slate Green
- CH-900 Black
- CH-1000 White
- CH-1010 Smokey Beige
- CH-1015 Blush Beige
- CH-1020 Antique Rose
- CH-1030 Ash White
- CH-1035 Summer Beige
- CH-1040 Weathered Sage
- CH-1045 Shadow Slate
- CH-1050 Antique Cork
- CH-1055 Pecos Sand
- CH-1065 Quarry Red
- CH-1070 Sandy Buff
- CH-1075 Rose Taupe
- CH-1080 Adobe Buff
- CH-1090 Sun Buff